

Acrylcem

Component - B for micro cement

Component B in water base for the micro cement mixture.

Characteristics

- Mixture life: \pm 60 minutes
- Opening time: \pm 15 minutes
- Dry touch: 2 – 4 hours

** These times are contemplated with 20°C and they can oscillate depending on the ambient temperature.*

Performances

- Density: 1.09 kg/l 25°C
- Value PH: 8 – 10
- Viscosity (25°C): 1500 - 2000
- Flashpoint: Not applicable
- Water base.

Enforcements

- For the dust micro cement mixture.
- Great resistance to ageing.
- Water base.
- Excellent behavior to abrasion.

Recomendations

- Application temperatures: 10 – 30°C.
- Do not add water to the product.
- Respect always the same **Acrylcem** percentage in the mixture.

Acrylcem

Component - B for micro cement

Usage way

FLOOR-Facades

Mixture proportion: 2 to 1 (2 powder parts and 1 **Acrylcem** part).

Mix the 2 components during 5 minutes with the indicated low revolutions whisk, until obtaining an homogenous mass, workable and without lumps and let it rest for 2 minutes.

Associated products

*Micro cement

*Micro mortar



Packaging

5 and 20 liters drums
Component B for Pavicem micro cement

Appearance

Liquid

Preservation

In the closed original container and sheltered from outdoor and
humidity: 1 year

⚠ IMPORTANT

The observations and prescriptions of this technical sheet, even corresponding to our best experience, should be considered, in any case, purely indicative, and must be tested by exhaustive practical applications; Therefore, before using the product, whoever is going to do it must establish whether or not it is suitable for the intended use, and assumes any responsibility that may arise from its use. Once the product is handled or applied, the manufacturer will not assume any claim, nor will it be responsible for the form, mode and conditions of application.