Padec Industrial Corundum®

Colored mortar for industrial paving

Cement, quartz sand, mineral corundum, pigments and additives.



Product

- High performances mortar
- · Excellent durability
- Road traffic and pedestrian traffic resistant
- Colored.

Observations

- The waiting times for application oscillate depending on the temperature, humidity and concrete kind.
- Protect all the easily stained zones with Protector Pavistamp (chests, kerbs. skirting...).
- With hot weather or wind use the superficial retarder Bryten CH to control quick humidity evaporation on the fresh concrete surface so that enables a perfect union between the mortar and concrete, avoiding the superficial fissures appearance.

Characteristics

- Padec industrial corundum application through sprinkling on fresh concrete.
- The mortar must be completely integrated on the fresh concrete.
- Avoid soaking the concrete with water.
- In the cold weather time, accelerate the concrete setting process with Hormidur-SC.
- After the first 24 hours approx. cut the expansion joints.

Performances (6 kg/m2)

- Kneading water (grey-c color): 12-14%
- Compression resistance: ≥60 N/mm2
- Bending resistance: ≥10 N/mm2
- Wear resistance: ≤21 N / mm2
- Slip UNU-ENV 12633: USRV36 Class 3
- Impact resistance, UNE-EN ISO 6272-1:
- **Height of fall: >1500 mm
 - **Value IR: IR=14,7 N·m
- Classification according CTE, Section SU1: Class 3
- Behavior against fire: A1 euroclass
- Designation EN-13813: CT-C60-F10-A21
- * These results are from standard essays with 6 kg/m2 and they can oscillate depending on the workplace conditions.

Enforcements

- High resistance colored mortar for the industrial paving to be applied on the fresh concrete.
- Treading layer with excellent resistance.
- Commercial premises, parking, industrial plants ...
- · Indoors and outdoors.

Supports

• On fresh concrete.

Finishes

- Polished, rustic, decorated.
- Hydrate layer (fresh on fresh).

Recommendations

- Application temperatures: 5-30 °C.
- The water percentage can oscillate depending on the used mixer.
- Do not add water once the product has been sprinkled over the fresh concrete.
- Respect, perimeter joint (min. 5 mm), expansion and fractionation.
- Avoid application with strong wind or direct insolation.

Execution conditions

- The base is properly compacted and it has obtained the approval from the Project management team to receive the concrete.
- The site management team or the property will always decide concrete thickness.
- The concrete will be manufactured in an authorized plant and will be transported with concrete trucks in 30 minutes, it will have a cone of fall of 6.5 to 8 cm, to avoid the increase of slag and the segregation of granules.
- In the minutes following the regularization of concrete, it is smoothed allowing water to rise by capillarity and ensure perfect adhesion between concrete and mortar.
- Outdoors do not apply with wind, rain risk or frost-thaw possibility.
- Avoid application with low temperatures during the hours following to the mortar application. It increases the efflorescence by carbonation appearance risk.

Padec Industrial Corundum®

Colored mortar for industrial paving

Usage way

- · Manual dusting
- · Mechanical dusting
- · Hydrated layer (fresh over fresh)







Trowelled Polished

Striped

Opcional: Once the expansion joints are opened and the pavement has no ponded water, apply without overloading 1-2 cured resin coats **F-300** or **F250, Paviplast epoxy.**

Associated products

- *Fiberglass
- *Hormidur SC
- *F-250
- *F-300
- *Protector Pavistamp
- *Bryten CH
- *Paviplast epoxi
- *Microspheres



Packaging

25 kg sack 1200 kg pallet (48 sacks)

Colors







Cement gray, red and green (others on demand)

Consumption

Manual sprinkling: 3 - 6 kg/m2

Mechanical sprinkling: 6 - 12 kg/m2

Hydrate layer (fresh on fresh): ±20 kg/ m2 and cm thickness

Preservation

In original closed container, and sheltered from outdoor and humidity: 1 year



The observations and prescriptions of this technical sheet, even corresponding to our best experience, should be considered, in any case, purely indicative, and must be tested by exhaustive practical applications; Therefore, before using the product, whoever is going to do it must establish whether it is suitable for the intended use, and assumes any responsibility that may arise from its use. Once the product is handled or applied, the manufacturer will not assume any claim, nor will it be responsible for the form, mode and conditions of application.