

Pavigrout R3®

Quick setting repair mortar

High resistance cements, selected arid, special additives and fiber reinforcement.



Product

- Thixotropic.
- Armed with fibers.
- Fit for concrete sanitation.
- Controlled retraction mortar.
- Immediate high resistance.
- Without fissures.

Observations

- Moisten well before applying **Pavigrout-R3**.
- Do not add any additive to the mortar.
- Do not apply **Pavigrout-R3** on plaster or painted surfaces.
- Do not add water when the mass begins the setting process.
- Do not apply where water may remain stagnant.
- When a second coat is necessary, apply before the first has set.

Usage characteristics

- Rest time after the kneading: 5 min.
- Mass life: 30-60 min. (20°C)
- Tolerated maximum thickness: 3-15cm (in 5 cm layers)
- Setting start: 2- 4 hours

**These times are contemplated with 20°C and they can oscillate depending on the ambient temperature.*

Performances

- Apparent dust density: 1.4 g/cm³
- Kneading water (in laboratory): 15%
- Mass density: 1.7 g/cm³
- Adherence for direct traction: ≥ 1.5 MPa
- Compression resistance: ≥ 25 MPa
- Chlorides determination: $\leq 0.05\%$
- Elasticity module in compression: ≥ 15 GPa
- Frost-thaw with salt immersion: ≥ 1.5 Mpa
- Capillary absorption: ≤ 0.5 kg / (m²xh^{0.5})
- Behavior against fire: A1 euroclass

** These results have been obtained with standard essays and they can oscillate depending on the workplace conditions.*

Enforcements

- Repair of columns, beams, cantilevers, pillars, balconies, degraded concrete zones..., due to armor corrosion and where a quick setting is required.
- Refill of external cracks and coatings on of buildings.
- For reparations needing an urgent operating disposal, like revoke edges, registration boxes or pipe embedded and holes reparations.
- Indoors and outdoors.

Supports

- Concrete and cement mortars.
- Standard concrete block.

Recommendations

- Application temperatures from 10 -30°C.
- The water percentage can oscillate depending on the used mixer.
- In zones where the armor iron appears, clean with sandblast or with a metallic plane, cover with anti- corrosion mortar **Pavifer** and let it get dry at least 1 hour.
- Do not apply **Pavigrout - R3** over smooth concrete supports (before rough out and open porous).
- Do not use with filling paste
- Eliminate the deteriorated concrete, with possible release until obtaining a solid support.

Pavigrout R3®

Quick setting repair mortar

Execution conditions

The supports must be healthy, stable and resistant and without dust, plaster, painting...

Eliminate the deteriorated concrete and in a degrading status until arriving to the solid, resistant and wrinkled support.

Before the **Pavigrout-R3**, application, soak until saturation and apply when the surface is without water

On structural reparations and with the armor appearance, sanitize with sandblast, eliminate the dust and cover with anti-corrosion mortar **Pavifer**, let it get dry at least 1 hour.

Over facings without absorption, very smooth or few absorbents, strip and open porous to secure a good adherence.

Avoid coating application with low temperatures, strong humidity, rain... In the following hours to the mortar application increases the carbonation efflorescence appearance risk.

Usage way

*Manual kneading:

Mix a sack **Pavigrout-R3** (25kg) with 3,5-4 liters clean water until obtaining a homogeneous mass.

*Projected with machine:

Mix the mortar with 15-20 % clean water approximately.

* In zones where the iron armor appears, clean and apply anti-corrosion mortar **Pavifer**, let it get dry at least 1 hour.

Apply the final layer **Pavigrout-R3**, eliminate the remaining with the palette and proceed to trowel.

**Place the glass fiber or metallic mesh in zones with fissures appearance risk.*

Associated products

*Pavifer

*Pavigrout-r4

*Pavigrout-r2

*Pavigrout fluid



Packaging

25 kg sack
1200 kg pallet (48 sacks)

Colors

White and grey

Consumption

±1.4 kg/m² and mm thickness

Preservation

In the closed original container and sheltered from outdoors and humidity: 1 year

⚠ IMPORTANT

The observations and prescriptions of this data sheet, although corresponding to our best experience, should be considered, in any case, purely indicative, and should be tested by exhaustive practical applications; therefore, before using the product, the user must establish whether or not it is suitable for the intended use, and assumes all liability that may arise from its use. Once the product has been handled or applied, the manufacturer shall not assume any claim whatsoever, nor any liability as to the manner, mode and conditions of application.