

Pavimper CB®

Component B for Pavimper-2C

Water-based liquid binder for powdered mortar reinforcement.

Product

- Quick setting.
- Waterproof and resistant.
- Without chlorides.
- Without retraction.
- It can be coated.

Enforcements

- For the **Pavimper-2C** mixture.
- For mortars and concretes reinforcement.
- Great resistance to ageing.
- Water base.
- Excellent behavior to abrasion.

Recommendations

- Application temperatures from: 10 – 30°C.
- Do not add water to the product.
- Respect always the same percentage during the mixture.

Performances

- Density: 1.09 kg/l 25°C
- Value PH: 8 – 10
- Viscosity (25°C): 1500 - 2000
- Flashpoint: Not applicable
- Water base
- Indoors and outdoors

Usage way

Mixture proportion:

- 24 kg **Pavimper-2C**
- 12 lt **Component B**

- Spill **Pavimper-2C** (dust) over **comp B** (liquid) and mix with a low revolution whisk, until obtaining a homogeneous, workable mass without lumps.

⚠ IMPORTANT

The observations and prescriptions of this data sheet, although corresponding to our best experience, should be considered, in any case, purely indicative, and should be tested by exhaustive practical applications; therefore, before using the product, the user must establish whether or not it is suitable for the intended use, and assumes all liability that may arise from its use. Once the product has been handled or applied, the manufacturer shall not assume any claim whatsoever, nor any liability as to the manner, mode and conditions of application.



Packaging

12 liters drum

Aspect

Liquid transparent

Preservation

In the closed original container and sheltered from outdoors and humidity: 1 year

Characteristics

Mass life: 2 hours

Opening time: 2 hours

Dry to touch: 5 – 7 hours (20°C)

* All the information described has been obtained from standard essays and it can oscillate depending on the workplace conditions.