Pavicolor Fine Joint

Colored mortar for thin joint (0 to 3 mm)

Cement, selected arid, synthetic resins, organic and inorganic additive and mineral pigments.



Product

- · Excellent workability
- · Crack free
- · Water resistant
- Mixing between colours is allowed

Observations

- Outdoors use Pavicolor Flex.
- For joints with more than 3 mm use Pavicolor Wide Joint.
- For Revistamp E joints use Pavicolor Wide Joint.

Characteristics

- Rest time after the kneading: 2 minutes
- · Cleaning maximum time: 30-60 minutes
- · Mass life: 60 minutes
- Operating disposal: 3-4 days

Performances

- Apparent dust density: 900-1.100 kg/m3
- Kneading water in laboratory: 30%
- Mass density: 1.6 g/m3
- Hardened product: 1.700-1.900 kg/mm3
- Compression resistance: ≥ 15 Mpa
- Bending resistance: ≥ 2,5 Mpa
- Capillarity: 2 g/dm2 · min1/2
- ** All the information described has been obtained with standard essays and it can oscillate depending on the workplace conditions.

Enforcements

- Colored mortar in thin layer for refill of joints from 0 to 3 mm, wide between ceramic pieces and nay kind of pavement or coating.
- · All kind of ceramic flagstones rejoint.
- · Indoor and outdoor.

Enforcement tips

- Application temperatures 5°C to 30°C.
- The percentage of water may vary depending on the mixer used.
- In joints of less than 1.5 mm apply as a grout.
- Always respect the same proportion of water, excess water will make cleaning difficult, as well as the final finish.
- Avoid application in direct sunlight, strong wind, risk of rain, freezing or thawing...
- Do not add any additives to the product.
- Always respect the perimeter, expansion and fractionation joints.

Execution conditions

- Joints between flagstones have to be clean, dry and without dust.
- The rejoint has to be made after 24–48 hours from the ceramic fixing.
- On applications over porous or absorbent surfaces, perform a treatment to the flagstones with **Protector Pavistamp**, before proceeding with the rejoint in order to avoid the pieces to get stained.
- Fit to be used with refillable pistol.
- Outdoors do not apply with direct insolation or strong wind.

^{*} These times can considerably oscillate depending on the ambient temperature.

Pavicolor Fine Joint

Colored mortar for thin joint (0 to 3 mm)

Usage way

Kneading water in paste:

5 Kg bag: \pm 1,5 water liters. 25 Kg sack: \pm 7,5 water liters.

Kneading water as grout:

5 Kg bag: ± 2 water liters.

25 kg bag: ±8 litres of water, knead manually or with an electric mixer until a homogeneous, lump-free dough is obtained. Leave to rest for 2 minutes.

Refill the joints between flagstones. Wait 30-60 minutes to eliminate the product remains.

Clean with a humid sponge and rinse with clean water until obtaining the final finish.

Associated products

- · Pavicolor flex
- · Pavicolor wide joint
- Pavicolor-HD
- Pavicolor-PLUS
- Pavicolor-ECO
- Revistamp-E



Packing

5kg Bag (in 20kg boxes)
18 boxes pallet (360 kg)
* 25 kg. Packages please consult

Color

Color chart

Consumption

(Example)
Joint wide 10 mm.
Joint depth 5 mm.

Flagstones 30x30 cm. Approx. 0,5 kg/m2 Flagstones 15x15 cm. Approx. 1,0 kg/m2 Flagstones 10x10 cm. Approx. 1,5 kg/m2

Conservación

25 kg sacks: 1 year. 5 kg bags: 2 years.

From the fabrication date, in the closed original package and sheltered from outdoors.



The remarks and prescriptions in this data sheet, although corresponding to our best experience, should in any case be considered purely indicative, and should be tested by exhaustive practical applications; therefore, before using the product, the user must establish whether or not it is suitable for the intended use, and assumes all liability that may arise from its use. Once the product has been handled or applied, the manufacturer shall not assume any claim whatsoever, nor any liability as to the manner, mode and conditions of application.