

# Pavicolor Plus

Universal mortar for joints refill (0 to 25 mm)

Special cements recycled arid, special additives and mineral pigments.



## Product

- Does not contain any biocides
- Deformable
- Resists efflorescence
- Excellent adhesion

## Observations

- Fungicide properties.
- Resists bacteriological attacks.
- Waterproof.

## Characteristics

- Rest time after the kneading: 2 minutes
- Cleaning maximum time: 30-60 minutes
- Mass life: 60 minutes
- Dry touch: 1- 2 hours
- Operating disposal: 3-4 days
- Total setting: > 7 days

*\*These results are contemplated at 20°C and may vary considerably depending on the ambient temperature.*

## Performances

- Dust density: 940 kg/m<sup>3</sup>
- Kneading water in laboratory: 30%
- Mass density: 1100 kg/m<sup>3</sup>
- Water absorption: <0,1 kg (m<sup>2</sup> min 0,5 )
- Retraction: 0,01 mm/m (UNE 83831 EX)
- Compression resistance: ≥21 Mpa
- Bending resistance: ≥5 Mpa

*\*\* All the information described has been obtained with standard essays and it can oscillate depending on the workplace conditions.*

## Enforcements

- Polyvalent mortar for joints between flagstones from 0 to 25 mm refill, in any kind of pavement, ceramic coating or stamped

### Revistamp E.

- All kind of ceramic flagstones rejoin.
- Indoors and outdoors
- Heating floor.

## Enforcement tips

- Application temperatures from 5°C to 30°C.
- The water percentage can oscillate depending on the used mixer.
- Kneading will be equal to a glue mortar consistency.
- Respect always the same water proportion, water excess will hinder the performance, as well as the cleaning and final finish.
- Avoid application in rainy or very wet weather, with frost risk or with direct insolation.
- Respect always the perimeter joint, expansion joint and division joint.

## Execution conditions

- Joints between flagstones have to be clean, dry and without dust.
- A water excess will hinder the mortar final performances.
- The rejoin has to be made after 24-48 hours from the ceramic fixing.
- Apply in small surfaces in order to be able to clean progressively.
- On applications over porous or absorbent surfaces, perform a treatment to the flagstones with **Protector Pavistamp** before proceeding with the rejoin in order to avoid the pieces to get stained.
- Fit to be used with refillable pistol.
- Outdoors do not apply with direct insolation or strong wind.

# Pavicolor Plus

Universal mortar for joints refill  
(0 to 25 mm)

## Usage way

### Kneading water in paste:

5 Kg bag:  $\pm 1,5$  water liters.

25 Kg sack:  $\pm 7,5$  water liters.

### Kneading water as a grout:

5 Kg bag:  $\pm 2$  water liters.

25 Kg sack:  $\pm 8$  water liters, knead manually or with electric whisk until obtaining a homogeneous mass and without lumps.

Let it rest during 2 minutes.

Refill the joints between flagstones, during the hardening start and without surface brightness, clean with a sponge.

Once the product is hardened, clean with clean water or a wet cloth.

## Associated products

- Pavicolor-HD
- Pavicolor-ECO
- Revistamp-E



## Packing

20 kg box (4 bags with 5 kg)

18 boxes pallet (360 kg)

\* 25 kg. Packages please consult.

## Color

Color chart

## Consumption

(Example)

Joint wide 10 mm

Joint depth 5 mm

Flagstones 30x30 cm. approx. 0,5 kg/m<sup>2</sup>

Flagstones 15x15 cm. approx. 1 kg/m<sup>2</sup>

Flagstones 10x10 cm. approx. 1,5 kg/m<sup>2</sup>

## Preservation

25 kg sacks: 1 year

5 kg bags: 2 years

From the fabrication date, in the closed original package and sheltered from outdoors.

## ⚠ IMPORTANT

The remarks and prescriptions in this data sheet, although corresponding to our best experience, should in any case be considered purely indicative, and should be tested by exhaustive practical applications; therefore, before using the product, the user must establish whether or not it is suitable for the intended use, and assumes all liability that may arise from its use. Once the product has been handled or applied, the manufacturer shall not assume any claim whatsoever, nor any liability as to the manner, mode and conditions of application.